

HONG KONG CONSTRUCTION INDUSTRY TRADE TESTING CENTRE 香港建造業工藝測試中心

Marble Worker (Polishing) Intermediate Trade Test Study Material for Written Test

(Version: IMP-SM-EN-01)



Version: IMP-SM-EN-01

Disclaimer

No part of this material may be reproduced or transmitted in any form or by any means without the written permission from the Construction Industry Council (CIC). Whilst reasonable efforts have been made to ensure the accuracy of the information contained in this material, the CIC nevertheless would encourage readers to seek appropriate independent advice from their professional advisers where possible and readers should not treat or rely on this material as a substitute for such professional advice for taking any relevant actions. The CIC will not assume any liability in relation to any loss or damage directly or indirectly resulted from unintended or/and unforeseeable use of this document.

This document is provided as reference for test preparation only. Under all circumstances all content in the official test papers, including but not limited to the terms and conditions therein, prevails.

The CIC reserves the right, at its sole and absolute discretion, to change, update or delete the contents in this document at any time without prior notice.

The CIC reserves all rights of final interpretation for any content in this document.

Enquiries

Enquiries on this material may be made to Hong Kong Construction Industry Trade Testing Centre at:

Address: 95 Yue Kwong Road, Aberdeen, Hong Kong


Tel: (852) 2100 9000 Fax: (852) 2100 9090 Email: hkcittc@cic.hk Website: www.cic.hk

Marble Worker (Polishing) Intermediate Trade Test Study Material for Written Test


This study material is a reference for candidate to prepare for attending written test in Intermediate

Trade Test:

- 1. The diameter of the disc commonly used in portable grinding machine is 100mm.
- 2. To cut marble panel, the commonly used tool is diamond blade.
- 3. The common thickness of a piece of marble for stone cladding is 20mm.
- 4. Stone flaming is applicable to granite.
- 5. The characteristic of slate is that it has an uneven surface.
- 6. Ivory stone is a kind of sandstone.
- 7. To remove stains on marble surface, ammonia powder can be used.
- 8. To fix broken marble, marble glue should be use.
- 9. Hydrogel is a kind of marble glue which is more adhesive.
- 10. The finest sandpaper is 1000 grit.
- 11. The correct way to use Chinese wax (bee's wax) is waxing it under high temperature.
- 12. The use of Chinese wax (bee's wax) is to mimic true lighting effect.
- 13. The edge of the stone element shown on the diagram is called full bullnose.



14. The edge of the stone element shown on the diagram is called DuPont.



Version: IMP-SM-EN-01

Version: IMP-SM-EN-01

- 15. Earmuffs is one of the personal protective equipment to protect one against noises.
- 16. In case of foreign object in the eye, clean water should be used to flush the foreign object out of the eye.
- 17. While working at height, in addition to the safety helmet, safety belt should be properly used.
- 18. According to Construction Site (Safety) Regulations, the contractor responsible for a construction site at which 5 or more workmen are employed shall provide and maintain so as to be readily accessible a separate first aid box or cupboard for every 50 workmen or part thereof employed on the site.
- 19. The correct work attitude is to maintain good attendance and never be absent from work on excuses or without any reasons.
- 20. After finishing works in everyday, tools and work site should be cleaned.

Precautions

This document is provided as reference for test preparation only. Under all circumstances all content in the official test papers, including but not limited to the terms and conditions therein, prevails. There are different versions of the test paper, content include but not limited to tools, materials, equipment, drawing, construction details or procedures and different simulated site environments. Candidates should refer to the official test documents during testing.

The CIC reserves the right, at its sole and absolute discretion, to change, update or delete the contents in this document at any time without prior notice.