

Plasterer

Intermediate Trade Test

Study Material for Written Test

(Version : IPT-SM-EN-02)



此文件關於批盪工中級工藝測試技術知識測試 (筆試) 內容參考資料。
如需索取此文件的中文版本，請致電 2100 9000 與香港建造業工藝測試中心聯絡。

Disclaimer

No part of this material may be reproduced or transmitted in any form or by any means without the written permission from the Construction Industry Council (CIC). Whilst reasonable efforts have been made to ensure the accuracy of the information contained in this material, the CIC nevertheless would encourage readers to seek appropriate independent advice from their professional advisers where possible and readers should not treat or rely on this material as a substitute for such professional advice for taking any relevant actions. The CIC will not assume any liability in relation to any loss or damage directly or indirectly resulted from unintended or/and unforeseeable use of this document.

This document is provided as reference for test preparation only. Under all circumstances all content in the official test papers, including but not limited to the terms and conditions therein, prevails.

The CIC reserves the right, at its sole and absolute discretion, to change, update or delete the contents in this document at any time without prior notice.

The CIC reserves all rights of final interpretation for any content in this document.

Enquiries

Enquiries on this material may be made to Hong Kong Construction Industry Trade Testing Centre at:

Address: 95 Yue Kwong Road, Aberdeen, Hong Kong

Tel: (852) 2100 9000

Fax: (852) 2100 9090



Email: hkcittc@cic.hk

Website: www.cic.hk

Plasterer Intermediate Trade Test

Study Material for Written Test

This study material is a reference for candidate to prepare for attending written test in Intermediate Trade Test:

1. The maximum thickness of plaster for interior ceiling should be 10mm thick.
2. Surface finishes work should be started at 7 days after completed the rendering coat.
3. If plastering is applying area by area of the floor, other area next beside the completed plastering area should be started at 24 hours after the completed one.
4. The main function of spatterdash is to enhance the bonding between the concrete surface and the plastering layer.
5. To control the verticality and level of plastering surface, levelling dot should be used.
6. The function of screed on walls during plastering is to control the thickness of coating.
7. Plastering is generally conducted layer by layer as it is more convenient for operation, and it decreases the chance of having cracks on the wall after solidification.
8. The reason to prepare a rough surface of undercoat during rendering is to increase the surface bonding for next coating.
9. To prepare rough rendering surface, rakes should be used to scratch the surface.
10. Cement mortar should be abandoned if it loses its plasticity.
11. The symbol shown in the diagram represents sand. 
12. The symbol shown in the diagram represents level. 
13. To measure vertically during plastering, plumb bob is commonly used.
14. During plastering, plastering trowel is used to smooth the mortar on wall surfaces.
15. In addition to safety helmet, safety belt should be worn when working at height.
16. Every board or plank forming part of a working platform should be not less than 25mm in thickness.

17. After finishing works in everyday, tools and work site should be cleaned.
18. When working in a group, the right attitude to work with colleagues is to be considerate, work together and develop good relationships.
19. The correct way to use safety harness is to attach the snap hook at higher level than user's waist.
20. In case of foreign object in the eye, clean water should be used to flush the foreign object out of the eye.

Precautions

This document is provided as reference for test preparation only. Under all circumstances all content in the official test papers, including but not limited to the terms and conditions therein, prevails. There are different versions of the test paper, content include but not limited to tools, materials, equipment, drawing, construction details or procedures and different simulated site environments. Candidates should refer to the official test documents during testing.

The CIC reserves the right, at its sole and absolute discretion, to change, update or delete the contents in this document at any time without prior notice.